General information:

INCI Name	Polyurethane-48
INCINAILE	Folyuletilalie-40
Ingredient category	Film former
Chemical description	Water-based polyurethane polymer (anionic) including 1.5% antimicrobial additive
Appearance	Milky dispersion
Solid content	30.0±2.0
рН	7.0±1.5
Viscosity	<1000 mPa.s

Sustainability profile:

- Biodegradability: Reached a mean biodegradation rate of 64% within 28 days (OECD 301 ready biodegradability test*).
- Microplastics status: out of scope (2019 ECHA restriction proposal).

Applications:

- Hair styling: styling aerosol, pumpspray, lotion, cream, gel cream & aerosol mousse
- Hair care: hair treatment & leave-on conditioner

Technical benefits:

- Flexible hold
- Style retention
- Wash resistance
- Waterproofing
- Frizz control
- Heat protection
- Straightening

Others:

- Suitable for *vegan* products.
- Suitable for *cruelty-free* products.
- Suitable for **biodegradable** formulas.
- Marketable in China*.
 - *Newly filed cosmetic ingredient under monitoring period.

Recommendations/Formulating tips:

Use level

3-10% as supplied



Covestro Deutschland AG Kaiser-Wilhelm-Allee 60 51373 Leverkusen Germany

cosmetics.covestro.com info@covestro.com



Compatibility

- pH: Products with pH between 4.5-8.0 can be formulated; ideally, we recommend adjusting the pH to the 6.0-8.0 range.
- **Salt:** Supports only low level of electrolytes; we recommend the use of maximum 0.5% of sodium chloride.
- Chelating agents: Compatible with state-of-the-art chelating agents.
- Ethanol: Compatible with ethanol; forms translucent solutions.
- Cationics: Limited compatibility depending on charge density. We recommend adding an amphoteric polymer (e.g. polyquaternium-39) to increase the compatibility with cationic polymers.
- **Non-ioninc polymers:** Compatible with non-ionic film formers such as PVP, VP/VA copolymer.
- Anionic polymers: Limited compatibility depending strongly on neutralization grade and charge density.
- **Propellants:** Compatible with DME; very limited compatibility with propane butane.

Process

- Add Baycusan® C 1008 at the end of the formulation process below 40 °C.
- We recommend homogenzing before addition of Baycusan® C 1008.
- We recommend adjusting the pH before the addition of Baycusan® C 1008. If necessary, pH could be adjusted with a diluted solution (at 10%) of either citric acid or sodium hydroxide after the addition of Baycusan® C 1008.

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product, unless explicitly stated otherwise.

Any samples provided by Covestro are for testing purposes only and not for commercial use. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request.

All information, including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release and indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. For more information on Covestro products in Cosmetic Applications, please refer to

https://solutions.covestro.com/-/media/Covestro/Solution%20Center/Brochures/PDF/COS_Disclaimer These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values.

Edition: 2022 · Printed in Germany

^{*}Test perfored on the polymer itself.