



Decovery® CQ 2110

Decovery® CQ 2110

Reducing emissions in parquet floor coatings



A partly bio-based binder for low-VOC wood flooring

Consumers increasingly seek natural-looking, textured interior finishes. In response, more and more architects are choosing wood as their preferred flooring material. At the same time, demand is growing for lower-emissions coatings for this wood flooring – driven by awareness of indoor air quality, plus updated labeling standards.

Improving environmental impact while protecting parquet floors

Decovery® CQ 2110 was created to address the demand for low-VOC parquet coating solutions. This water-based binder enables a low solvent demand. As such, it enables formulations that comply with **EMICODE® EC1 PLUS**. It is also Nordic Swan- and Ecolabel-compliant.

All this while still protecting the beauty of wood flooring: in parquet coatings, **Decovery® CQ 2110** produces a neutral-colored finish with excellent chemical resistance and mechanical properties. This includes resistance to abrasion, black heel marks, and scuffs.

Curious?

Find out more on our Solution Center:



Covestro Deutschland AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany

solutions.covestro.com



Key benefits:

- 36% bio-based content (C14-certified)
- Low solvent demand
- Can be formulated into coatings compliant with **EMICODE® EC1 PLUS**
- Nordic Swan- and Ecolabel-compliant
- Excellent mechanical properties and chemical resistance

Decovery® CQ 2110 at a glance

- **Chemical base:** Aliphatic urethane dispersion
- **Bio-based content:** 36% (C14-certified)
- **Solids:** 35%
- **MFFT:** 18°C

Reduced solvent demand

1K PARQUET LACQUER	DECOVERY® CQ 2110	DECOVERY® CQ 2110 / DECOVERY® SP 7433 (70/30)
Binder	87.32	87.32
Water	6.98	9.56
Dowanol DPnB	0.96	0.88
Dowanol DPM	3.83	1.32
Coapur 3025	0.31	0.31
Byk 028	0.51	0.51
Byk 347	0.10	0.10
Solvent % on binder	5.5	2.5
Solvent % on formulation	4.8	2.2

Guide formulations available on request

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product, unless explicitly stated otherwise. [EMEA only: If the intended use of the product is for the manufacture of a pharmaceutical/ medicinal product, medical device¹ or of pre-cursor products for medical devices or for other specifically regulated applications which leads or may lead to a regulatory obligation of Covestro, Covestro must explicitly agree to such application before the sale]. Any samples provided by Covestro are for testing purposes only and not for commercial use. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information, including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release and indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values.

¹Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

Edition: June 2024 - all images created by AI