INSQIN® new partially bio-based and mass balanced polyurethane dispersions for textile coatings.

Impranil® CQ

bluesign SYSTEM PARTNER

ROADMAP TO ZERO By ZDHC

covestro

Impranil® CQ

High performance enabled by nature: New partially bio-based and mass balanced polyurethane dispersions for textile coatings

Increasingly, sustainability is affecting the product and raw material purchasing decisions of customers, brand owners, and consumers. Biomass is already the raw material basis for around 10% of all chemical products. New technologies, cooperative agreements and product developments will enable the textile coating industry to move forward in using more products based on renewable resources.

Covestro has developed a technology to significantly raise the content of alternative resources in polyurethane dispersions (PUDs). This makes new levels of sustainability possible for PU-coated textile materials. Thanks to this development, it is now possible for manufacturers to produce coated fabrics with a lower content of fossil-based raw materials. These partially bio-based or mass balanced products offer the same level of properties as products based on traditional raw materials.

Synthetic coated textile structure



Sustainability targets



Key benefits of **Impranil® CQ** PUDs:

- 34%-67% alternative carbon content derived from non-fossil-based inputs for partially bio-based PUDs.
- Up to 78 wt.-% alternative raw material share for mass-balance certified PUDs containing recycled bio-circular attributed content.
- Good light fastness, excellent resistance to abrasion.
- Excellent perceptual quality.
- More sustainable thanks to reduced CO_2 footprint.
- Better water and energy utilization during production.
- Suitable to be used for a variety of textile coating applications.
- Excellent compatibility with conventional PUDs.
- Mass-balance products are chemically and physically identical to the conventional products and can be easily implemented within your production process, with no technical risk and no further approvals.

Product	Type	Verification process*	Alternative carbon content share [%] / alternative raw material share [wt.-%]**	Solid content [%] (DIN EN ISO 3251)	100% Modulus [MPa] (DIN 53504)***	Tensile Strength [MPa] (DIN 53504)***	Elongation at Break [%] (DIN 53504)***
Impranil® CQ 2566	Partially bio-based polyether	Segregation approach	~67	29-31	5	52	760
Impranil® CQ DL 1878	Partially bio-based polyester	Segregation approach	~56	50	1.7	12	800
Impranil® CQ DL 519	Partially bio-based polyester	Segregation approach	~38	40	9	40	450
Impranil® CQ DLS/1	Partially bio-based polyester	Segregation approach	~50	50	2.5	30	800
Impranil® CQ DLU	Partially bio-based polyether/ polycarbonate	Segregation approach	~34	54-56	2.5	25	700
Impranil® CQ DLP-R	Polyester	Mass balance approach	~78	48-52	0.9	10	1100
Impranil® CQ DLU MS	Polyether/Polycarbonate	Mass balance approach	~48	58-62	2-3	30	700

*Segregated process allows traceability of renewable feedstock in end products; ISCC PLUS certification to secure transparency, trustworthiness of the Mass Balance method
**Segregation approach: bio-based carbon content share [%], expressed as fraction of total carbon content, calculated internally and analytically verified through external C14 measurement; Mass balance approach: Alternative raw material share [wt.-%] (on solids, without water). The percentage refers to the proportion of bio-circular attributed content relative to the total mass of the product in its delivery form, calculated using the ISCC PLUS certified mass balance.
***These values provide general information and are not part of the product specification.

Covestro Deutschland AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany

insqin.com

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product, unless explicitly stated otherwise. [EMEA only: If the intended use of the product is for the manufacture of a pharmaceutical/ medicinal product, medical device[1] or of pre-cursor products for medical devices or for other specifically regulated applications which lead or may lead to a regulatory obligation of Covestro, Covestro must explicitly agree to such application before the sale.] Any samples provided by Covestro are for testing purposes only and not for commercial use. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information, including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release and indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

[1] Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

Edition: 2026